



Exhibit C

**Examples 19 and 37 of
Moffatt et al. U.S. Patent No. 5,508,237**

Mol %	19	37
SiO ₂	64.7	64.0
Al ₂ O ₃	15.1	14.7
B ₂ O ₃	7.7	9.6
MgO	3.9	4.2
CaO	4.2	2.9
SrO	3.2	3.4
BaO	1.2	1.2
CTE*	32.2	31.2
RO/Al ₂ O ₃	0.83	0.80

*x 10⁻⁷/°C

BEST AVAILABLE COPY